

ARTIFACT SHEET

Enter artifact number below. Artifact number is application number + artifact type code (see list below) + sequential letter (A, B, C ...). The first artifact folder for an artifact type receives the letter A, the second B, etc.. Examples: 59123456PA, 59123456PB, 59123456ZA, 59123456ZB

59014518 BA

Indicate quantity of a single type of artifact received but not scanned. Create individual artifact folder/box and artifact number for each Artifact Type.

☐

CD(s) containing:

computer program listing

Doc Code: Computer

pages of specification

and/or sequence listing

and/or table

Doc Code: Artifact

content unspecified or combined

Doc Code: Artifact

☐

Artifact Type Code: P

☐

Artifact Type Code: S

☐

Artifact Type Code: U

☐

Stapled Set(s) Color Documents or B/W Photographs

Doc Code: Artifact

Artifact Type Code: C

☐

Microfilm(s)

Doc Code: Artifact

Artifact Type Code: F

☐

Video tape(s)

Doc Code: Artifact

Artifact Type Code: V

☐

Model(s)

Doc Code: Artifact

Artifact Type Code: M

☒

Bound Document(s)

Doc Code: Artifact

Artifact Type Code: B

☐

Confidential Information Disclosure Statement or Other Documents marked Proprietary, Trade Secrets, Subject to Protective Order, Material Submitted under MPEP 724.02, etc.

Doc Code: Artifact

Artifact Type Code X

☐

Other, description: _____

Doc Code: Artifact

Artifact Type Code: Z

The
United
States
of
America



The Commissioner of Patents
and Trademarks

*Has received an application for a patent
for a new and useful invention. The title
and description of the invention are en-
closed. The requirements of law have
been complied with, and it has been de-
termined that a patent on the invention
shall be granted under the law.*

Therefore, this

United States Patent

*Grants to the person or persons having
title to this patent the right to exclude
others from making, using or selling the
invention throughout the United States
of America for the term of seventeen
years from the date of this patent, sub-
ject to the payment of maintenance fees
as provided by law.*

Bence Lehman

Commissioner of Patents and Trademarks

Shane Terry

Attest



US005472790A

United States Patent [19]**Thompson**[11] **Patent Number:** **5,472,790**[45] **Date of Patent:** **Dec. 5, 1995**[54] **PREPARATION AND TRANSFER SHEET**[75] **Inventor:** **Roderick Thompson, Solana Beach, Calif.**[73] **Assignee:** **New Age Products, Inc., San Marcos, Calif.**[21] **Appl. No.:** **259,006**[22] **Filed:** **Jun. 13, 1994****Related U.S. Application Data**[63] **Continuation-in-part of Ser. No. 994,665, Dec. 22, 1992, abandoned.**[51] **Int. Cl.⁶** **B32B 27/00**[52] **U.S. Cl.** **428/500; 428/195; 428/220; 428/332; 428/337; 428/339; 428/411.1**[58] **Field of Search** **430/281, 288; 428/131, 323, 195, 220, 332, 337, 500, 339, 411.1, 216, 35.7; 156/201; 427/393.5**[56] **References Cited****U.S. PATENT DOCUMENTS**

2,778,324	1/1957	Mattson	107/46
2,935,107	5/1960	Bertelsen	146/215
3,448,913	6/1969	Wolff	229/14
3,837,634	9/1974	Cobb	269/289
4,192,494	3/1980	Mima	269/289 R

FOREIGN PATENT DOCUMENTS

54-063972 5/1979 Japan .

1185226	7/1989	Japan .
4043506	2/1992	Japan .
882231	3/1988	South Africa .
2248177	4/1992	United Kingdom .

OTHER PUBLICATIONS

"Encyclopedia of Polymer Science and Engineering", 1988, Wiley & Sons, vol. 13, pp. 481-486. See table 15.

"Encyclopedia of Polymer Science and Engineering", Wiley & Sons, vol. 7, p. 89.

"Encyclopedia of Polymer Science and Technology", vol. 11, pp. 609-613.

Counter Maid Product Brochure, published 1983 (see transmittal letter).

Primary Examiner—Patrick J. Ryan*Assistant Examiner*—William A. Kaynski*Attorney, Agent, or Firm*—Brown, Martin Haller & McClain

[57]

ABSTRACT

A thin polypropylene sheet is extruded flat, with a thickness in the range of 0.008 to 0.060 inches with a Rockwell hardness between 72 and 90 and a flexural modulus between 55,000 psi and 200,000 psi. The resultant surface may be utilized for cutting and chopping foods. A sharp knife will penetrate, but not perforate, the sheet material to not dull the knife while maintaining the integrity of the surface. When flexed around its longitudinal centerline, the sheet material develops substantial cantilever beam strength, so as to transport food articles after preparation into an appropriate container.

9 Claims, 1 Drawing Sheet